

PP0420

References :

Diffusing additive: PP0420

Definition :

Additive creating a light diffusion effect, making the clear PU resins whiter while maintaining the light permeability of the final part.

Compatible with:

- PRC1810-PRC1819
- PRC1710-PRC1719
- PRC120

Physical properties of the component :

	Diffusing additive PP0420
Aspect - Colour	White to beige thick paste
Density at 25°C According to MO-032	2,3

Application properties :

In order to maintain the final properties of the clear resins, the diffusing additive is involved in the system polymerisation. Rehomonise the product before use.

Depending on the selected resin, an adjustment of the mixing ratio has to be realised, according to the rate of applied diffusing additive to get the expected aspect and effect. The below chart shows the maximum of recommended rate in the clear resins.

Evolution of the mixing ratio according to the selected resin :

	Polyol	Diffusing additive	Isocyanate
PRC1810-PRC1819	56	0	100
	50	10	100
PRC1710-PRC1719	60	0	100
	55	10	100
PRC120	100	0	102
	93	10	102

It is recommended to realise a pre-mix of the diffusing additive with the polyol component of the selected resin. Then use this premix product as the standard product, and by applying the new mixing ratio.

The values mentioned on this document are based on tests and researches carried out in SYNTHENE's laboratory, in precise conditions. This document cannot be, in any case, considered as a specification data sheet. It is the responsibility of the users to check the suitability of the product in their own conditions, defined and tried by themselves. Synthene company disclaims any responsibility for any consequence occurred by the use of this product.



45 Ferme de L'Evêché - CS 20308
60723 Pont-Sainte-Maxence CEDEX - FRANCE
Tel : + 33 3 44 31 72 00
Fax : + 33 1 57 67 44 58
E-mail : contact@synthene.com
<http://www.synthene.com>

Hygiene and safety instructions for using :

Wearing appropriate safety clothes and accessories (gloves, glasses and mask) is highly recommended.

Work in a ventilated room.

For more information, please read the Medical and Safety Data Sheet of the material.

Packaging :

PP0420 : Metallic box of 0,5 kg

Storage :

2 years in the original and unopened container, stored between 5 and 30 °C and kept away from moisture and UV-radiation.

The values mentioned on this document are based on tests and researches carried out in SYNTHENE's laboratory, in precise conditions. This document cannot be, in any case, considered as a specification data sheet. It is the responsibility of the users to check the suitability of the product in their own conditions, defined and tried by themselves. Synthene company disclaims any responsibility for any consequence occurred by the use of this product.