


SYNTHENE SAS

45 Ferme de L'Evêché
60723 Pont-Sainte-Maxence
France

T +33 3 4431-7200
@ comm@synthene.com
» www.synthene.com



handout **SYNTH3D+** **PU PRINT 50 – 80 A**





PRELIMINARY TECHNICAL DATA

PRODUCT NAME	UNIT	NORM	PU PRINT 50 A	PU PRINT 65 A	PU PRINT 70	PU PRINT 80
Hardness	Shore A	ISO 868 : 2003	50	64	72	82
Elongation at break at 23 °C	%	ISO 37 : 2012	851	1 114	940	1 105
Tensile strength at break at 23 °C	MPa	ISO 37 : 2012	5,3	8,5	9,2	13
Tear resistance at 23 °C	KN/m	ISO 34 : 2015	21,2	32,7	45	53,5



Do you have a question ?
Just ask us!

+33 3 44 31 72 00

comm@synthene.com

DEVELOPED IN
PARTNERSHIP WITH

