

45 Ferme de L'Evêché - CS 20308 60723 Pont-Sainte-Maxence CEDEX - FRANCE Tel : + 33 3 44 31 72 00 Fax : + 33 1 57 67 44 58 E-mail : contact@synthene.com http://www.synthene.com

# FASTELAST

### **References**:

Polyol: SL035000-FASTELAST 35A-POLYOL Polyol: SL093000-FASTELAST 93A-POLYOL

#### **Definition** :

## → FASTELAST system:

Three component polyurethane elastomer designed for the production of technical parts and soft prototypes. This system is based on 2 polyols and 1 isocyanate. It offers a large variety of hardnesses, ranging from a colourless 35 Shore A elastomer to a whitish 93 Shore A semi-rigid material, while keeping a high level of properties through the different possible hardnesses.

REACH-compatible product, meeting the requirements of the European Directives:

- 2011/65/EU 2015/863 2017/2102/UE (RoHS 1 and 2)
- 2002/96/EC (WEEE)
- 2000/53/EC (ELVs)
- 2000/11/EC

#### **Properties :**

- Short demoulding time
- Low viscosity
- Colourable material
- Good elongation at break
- Very good tear resistance, even notched

#### Average physical properties of the components :

References	Aspect - Colour	Brookfield LVT viscosity at 25°C in mPa.s According to MO-051	Density at 25°C According to MO-032
SL035000	Colourless Transparent liquid	350	1,04
SL093000	Colourless Transparent liquid	300	1,04
SL000935	Colourless to yellowish transparent liquid	500	1,03

The values mentioned on this document are based on tests and researches carried out in SYNTHENE's laboratory, in precise conditions. This document cannot be, in any case, considered as a specification data sheet. It is the responsibility of the users to check the suitability of the product in their own conditions, defined and tried by themselves. Synthene company disclaims any responsibility for any consequence occurred by the use of this product.

Isocyanate: SL000935-FASTELAST-ISO



45 Ferme de L'Evêché - CS 20308 60723 Pont-Sainte-Maxence CEDEX - FRANCE Tel : + 33 3 44 31 72 00 Fax : + 33 1 57 67 44 58 E-mail : contact@synthene.com http://www.synthene.com

#### Processing properties depending on the hardness :

Hardness	35A	45A	50A	60A	65A	75A	80A	86A	93A
SL035000 FastElast 35 A Polyol	100	90	85	75	60	45	30	10	
SL093000 FastElast 93 A Polyol		10	15	25	40	55	70	90	100
SL000935 FastElast 35-93 A Isocyanate	32	39	43	50	58	69	79	93	100
Brookfield LVT viscosity at 25°C (mPa.s) According to MO-051	350	310	310	300	300	300	300	300	300
Potlife on 200g at 25°C According to MO-062	16 min.	12 min.	13 min.	10 min.	10 min.	8 min.	10 min.	7 min.	6 min.
Potlife on 200g at 40°C According to MO-062	8 min.	7 min.	7 min.	6 min.	5 min.	5 min.	4 min.	4 min.	3 min.
Demoulding time at 70°C Curing in a 70°C mould	2h	1h	1h	1h	1h	1h	1h	1h	1h

The polyols and the isocyanate components crystallize under 15°C. Place them in an oven at 70°C during approximately 1 hour, or at 40°C for 16 hours. Shake them and check that the products are completely homogeneous before use.

#### Average mechanical and thermal properties of the cured material :

• Average values obtained on specimens after curing: 1h at 70°C + 7 days at room temperature \* Average values measured on specimens after curing: 2h at 70°C + 7 days at room temperature

Shore A hardness ISO 868	35*	45	50	60	65	75	80	86	93
Shore D hardness ISO 868									50
Working temperature (°C)	-20/+80	-20/+80	-20/+80	-20/+80	-20/+80	-20/+80	-20/+80	-20/+80	-20/+80
Maximum casting thickness (mm)	30	30	30	30	30	30	20	20	20
Elongation at break at 23°C (%) ISO 37	530	700	730	750	770	715	880	680	616
Tensile strength at break at 23 °C (MPa) ISO 37	1,8	3,7	4,9	7,1	8,3	14,5	15	26	22
<b>Tear resistance at 23°C</b> (kN.m-1) ISO 34	7,8	13,4	20	25	30	54	55	64	66

The values mentioned on this document are based on tests and researches carried out in SYNTHENE's laboratory, in precise conditions. This document cannot be, in any case, considered as a specification data sheet. It is the responsibility of the users to check the suitability of the product in their own conditions, defined and tried by themselves. Synthene company disclaims any responsibility for any consequence occurred by the use of this product.



## Hygiene and safety for using :

Wearing safety clothes and accessories (gloves, glasses) is recommended. Work in a ventilated room. For more information, please read the Medical and Safety Data Sheet of the material.

### **Operating conditions :**

Make sure that all the components are homogeneous before using. Depending on the transport and storage conditions, crystallization can happen in both the polyols and the isocyanate components. In this case, place in an oven at 70°C until the product is homogeneous. In order to avoid any re-crystallization phenomenon, it is recommended to store the opened containers at 40°C, even if the products are going to be consumed during the following days.

For the lower hardnesses and small quantities (<130g), it is recommended to weigh the polyols and the isocyanate components directly in the lower cup before starting the vacuum pump.

In case of dye or pigment addition, make sure to realise a compatibility test before using, particularly on the lower hardnesses.

## → Application process in a vacuum casting machine :

1. Preheat the polyaddition silicone mould at 70°C.

2. Rehomogenise and weigh the separated components (upper cup : Iso / lower cup : Polyol), with addition of the necessary residual quantity in the upper cup. Then, put the cups inside the vacuum casting machine.

If a pigment is added, it should imperatively be mixed to the polyol component. A 1 to 3% rate of the total product quantity (polyol + isocyanate) is recommended.

- 3. Degas the products during 10 minutes, with agitation in the lower cup (Polyol).
- 4. Stop the agitation and pour the content of the upper cup (Iso) into the lower cup (Polyol).
- 5. Start the agitation and mix for at least 1 minute.
- 6. Slightly release the vacuum in the chamber to a pressure of about 100 hPa (0,1bar).
- 7. Cast the mixture into the silicone mould until complete filling.
- 8. Break the vacuum back to atmospheric pressure.
- 9. Place the mould in an oven at 70°C.
- 10. Demoulding is possible after :
  - 1 or 2 hours at 70°C, depending on the hardness
- 11. The final hardness and mechanical properties of the material are obtained after :
  - Total curing time : 1 or 2h at 70°C + 7 days at room temperature

## → Application process with hand casting:

1. Pre-heat the polyaddition silicone mould at 70°C. The mould must be totally dry, without any trace of moisture.

2. Rehomogenise the polyol and the isocyanate. If a pigment is added, it should imperatively be mixed to the polyol component. A 1 to 3% rate of the total product quantity (polyol + isocyanate) is recommended.

3. Weigh the components, depending on the chosen hardness, mix the 2 polyols first. Mix them with a spatula or a low-speed rotational mixer.

The values mentioned on this document are based on tests and researches carried out in SYNTHENE's laboratory, in precise conditions. This document cannot be, in any case, considered as a specification data sheet. It is the responsibility of the users to check the suitability of the product in their own conditions, defined and tried by themselves. Synthene company disclaims any responsibility for any consequence occurred by the use of this product.



4. Degas the mixture under vacuum.

5. Cast the product on the support or inside mould. Once the casting is done, let the polymerisation happen at room temperature to help the self-degasification of the product. Then, place the mould in an oven at 70°C.
6. Demoulding is possible after :

- 1 or 2 hours at 70°C, depending on the thickness of the part.
- 7. The final hardness and mechanical properties of the material are obtained after :
  - Total curing time : 1 or 2h at 70°C + 7 days at room temperature

#### Packaging:

- SL035000 FastElast 35A Polyol : box of 6 x 1 kg
- SL093000 FastElast 93A Polyol : box of 6 x 1 kg
- SL000935 FastElast Isocyanate : box of 6 x 1 kg
- FastElast System : box of 4 x (1 kg SL035000 + 1 kg SL093000 + 1 kg SL000935)

#### Storage:

Shelf life for unopened packagings, stored in their original containers between 15 and 25 °C.

- Polyols : 12 months
- Isocyanate : 6 months

Once the packaging is opened, it must be closed back tightly, on a hermetic, moisture-free way, after each use, if possible under an inert atmosphere.

The values mentioned on this document are based on tests and researches carried out in SYNTHENE's laboratory, in precise conditions. This document cannot be, in any case, considered as a specification data sheet. It is the responsibility of the users to check the suitability of the product in their own conditions, defined and tried by themselves. Synthene company disclaims any responsibility for any consequence occurred by the use of this product.