




SYNTHENE SAS

45 Ferme de L'Evêché  
60723 Pont-Sainte-Maxence  
France

T +33 3 4431-7200  
@ comm@synthene.com  
» www.synthene.com



# SYNTH3D+ PUprint





## PRELIMINARY TECHNICAL DATA

| PRODUCT NAME                       |         |              | PU PRINT 50A | PU PRINT 65A | PU PRINT 70A | PU PRINT 80A |
|------------------------------------|---------|--------------|--------------|--------------|--------------|--------------|
| Hardness                           | Shore A | ISO 868:2003 | 50           | 64           | 72           | 82           |
| Elongation at break at 23°C        | %       | ISO 37:2012  | 851          | 1 114        | 940          | 1 105        |
| Tensile strength at break at 23 °C | MPa     | ISO 37:2012  | 5,3          | 8,5          | 9,2          | 13           |
| Tear resistance at 23°C            | KN/m    | ISO 34:2015  | 21,2         | 32,7         | 45           | 53,5         |